

TWO COLOURS



ONE DIRECTION

Polypropylene

**TATREN HG 10 07**

Homopolymer for general purpose

\*\*\*\*\*

**Description**

**TATREN HG 10 07** is homopolymer of good processing stability and excellent spinning properties. It is characterised by broad processing window and it enables to process this grade by different processing technologies – fibres, cast film and injection moulding. **TATREN HG 10 07** contains standard stabilisation additive package. It does not contain nor slip neither antiblocking agent.

**Applications**

**TATREN HG 10 07** is intended especially for staple fibres production. It is also suitable for cast film production as core layer at co-extrusion and for injection moulding of sanitary equipments, caps, closures and small technical items. This grade is partially suitable for sheet extrusion and thermoforming applications and for compounding.

**TATREN HG 10 07** is suitable for food contact. The product complies with Food Contact Regulations.

**Properties**

	Test method	Unit	Typical value
MFR (230 °C/2.16 kg)	ISO 1133	g/10 min	10
Tensile strength at yield *	ISO 527-1,2	MPa	35.5
Tensile elongation at yield *	ISO 527-1,2	%	9
Modulus of elasticity in tension *	ISO 527-1,2	MPa	1750
Flexural modulus *	ISO 178	MPa	1650
Izod impact strength (notched, 23 °C) *	ISO 180/1A	kJ/m <sup>2</sup>	3
HDT (0.46 MPa) *	ISO 75-1,2	°C	90
Rockwell hardness *	ISO 2039/2	R scale	102

\* Typical properties, not to be used as specification. Average mechanical property values of several measurements carried out on standard injection-moulded test specimens prepared in accordance with ISO 1873-2.



## Processing

**TATREN HG 10 07** can be processed on standard extrusion and injection moulding machines.

Recommended processing temperatures are 210 – 260 °C.

## Storage and Handling

Pellets are packed in 25 kg PE-LD bags and transported on shrink-wrapped pallets at eligible load of polymer 1250 or 1375 kg. Heat treated pallets are available as well. Transportation in a road silo or rail silo is also available. For more detailed information please contact Sloznaft Petrochemicals and TVK sales representative.

Since polypropylene is a combustible substance, the fire safety rules applicable for combustible materials in warehouses and store rooms should be observed.

If polymer is stored in conditions of high humidity and fluctuating temperatures, then atmospheric moisture can condense inside the packing. If it happened, it is recommended the pellets to be dried before use. During the storage polypropylene should not be exposed to UV radiation. Producer does not take responsibility for any damages caused by adverse storage.

## REACH Statement

Polymers are exempt of REACH registration. However their raw materials which mean monomers, catalysts and most additives have been pre-registered. SPC/TVK is committed to fully respect this new legislation and will only use REACH compliant raw materials. At this point in time SPC/TVK polypropylene TATREN/TIPPLEN, do not contain any substances specifically identified as SVHC at levels greater than 0.1 %.

## Safety

See MSDS.

## Recycling

Polypropylene resins are suitable for recycling using modern recycling methods.

In-house production waste should be kept clean to facilitate direct recycling.

## Disclaimer

The information provided in this publication has been compiled to the best of our present knowledge. However, in view of the various applications of polypropylene resins and the equipment used, the processing conditions may differ.

The recommendations and data herein are to be construed as informational only and do not relieve users from carrying out their own tests and experiments prior to processing in order to check suitability for a specific use. It is the responsibility of those to whom we supply our products to ensure that any proprietary rights and existing laws and legislation are observed. Our products are under continuous development, therefore we reserve the right to change the information presented in this brochure at our own discretion. The REACH statement herein does not constitute legal advice. The REACH statement is provided for informational purpose only.

TIPELIN TIPOLEN TIPPLEN TATREN BRALEN

The joint product portfolio of TVK and Sloznaft Petrochemicals provide infinite opportunities

MEMBERS OF THE MOL GROUP



**MANUFACTURER**

Slovnaft Petrochemicals, s.r.o.  
Vlčie hrdlo 4846  
824 12 Bratislava  
Slovak Republic

Internet: <http://www.slovnaft.sk>

E-mail: [info@slovnaft.sk](mailto:info@slovnaft.sk)

**CUSTOMER SERVICE**

Slovnaft Petrochemicals, s.r.o.  
Polymer Marketing and Sales

Telephone: + 421 2 4055 6836, + 421 2 4055 6941

Fax: + 421 2 5859 9825

E-mail: [jana.moncekova@petchem.sk](mailto:jana.moncekova@petchem.sk)  
[zuzana.kramarova@petchem.sk](mailto:zuzana.kramarova@petchem.sk)

**SALES ORGANIZATION**

Slovnaft Petrochemicals, s.r.o.  
Polymer Marketing and Sales  
Vlčie hrdlo 4846  
824 12 Bratislava  
Slovak Republic

Telephone: + 421 2 5859 7515, + 421 2 5859 7682

Fax: +421 2 5859 7224

TIPELIN TIPOLEN TIPPLEN TATREN BRALEN

The joint product portfolio of TVK and Slovnaft Petrochemicals provide infinite opportunities

MEMBERS OF THE MOL GROUP



**Slovnaft**  
PETROCHEMICALS



**TVK**

**TVK Inter-Chemol GmbH.**  
Felnerstrasse 5.  
D-60322 Frankfurt am Main  
Germany  
**Telephone:** +49 69 154 04 12  
**Fax:** +49 69 154 04 41  
**E-mail:** [gaboragoston@tvkic.de](mailto:gaboragoston@tvkic.de)

**TVK Italia S.r.L.**  
Via P. Teulíe 1.  
I-20136 Milano  
Italy  
**Telephone:** +39 02 58 30 55 23  
**Fax:** +39 02 58 30 34 92  
**E-mail:** [tvkitaly@energy.it](mailto:tvkitaly@energy.it)

**TVK-France**  
182 Avenue Charles De Gaulle  
F-92200 Neuilly sur Seine  
France  
**Telephone:** +33 14 745 63 60  
**Fax:** +33 14 745 45 10  
**E-mail:** [kacsandi@free.fr](mailto:kacsandi@free.fr)  
[tvk.france@orange.fr](mailto:tvk.france@orange.fr)

**TVK Ukraine**  
04128 Kiev  
ul. Tupoleva 19, office 303  
**Telephone:** +380 44 374 00 80  
**Fax:** +380 44 374 00 90  
**E-mail:** [office@tvkukraine.eu](mailto:office@tvkukraine.eu)

**TVK Polska Sp. z o.o.**  
ul. Wawozowa 23/12  
PL 02-796 Warszawa  
Poland  
**Telephone:** +48 22 545 70 70  
**Fax:** +48 22 545 70 60  
**E-mail:** [tvkpolska@tvkpolska.pl](mailto:tvkpolska@tvkpolska.pl)  
[www.tvkpolska.pl](http://www.tvkpolska.pl)

**MOL- Austria Handels GmbH.**  
Gartenbaupromenade 2/6  
A-1010 Wien  
Austria  
**Telephone:** +43 1 515 991 120  
+43 1 515 991 121  
**Fax:** +43 1 513 37 55 1120  
+43 1 513 37 55 1121  
**E-mail:** [JHauk@MOL.hu](mailto:JHauk@MOL.hu)

**SC. MOL Romania P.P. SRL**  
Str. Danielopolu 4-6  
ET2 Sector 1 Cod 014 134  
Bucuresti, Romania  
**Telephone:** +40 21 204 85 00  
+40 21 204 85 02  
**Fax:** +40 21 232 1059  
**E-mail:** [ematei@molromania.ro](mailto:ematei@molromania.ro)  
[petchem@molromania.ro](mailto:petchem@molromania.ro)

**Other European Countries**  
H-3581 Tiszaújváros  
P.O.B. 20.  
**Telephone:** +36 49 52 21 18  
**Fax:** +36 49 52 24 10  
**E-mail:** [plokai@tvk.hu](mailto:plokai@tvk.hu)

June 2009

TIPELIN TIPOLEN TIPPLEN TATREN BRALEN

The joint product portfolio of TVK and Slovnaft Petrochemicals provide infinite opportunities

MEMBERS OF THE MOL GROUP



**Slovnaft**  
PETROCHEMICALS

