

TWO COLOURS



**ONE** DIRECTION

Polyethylene  
**TIPELIN 7300B**

Bimodal HDPE for blow moulding

\*\*\*\*\*

### Description

**TIPELIN 7300B** is a high density bimodal polyethylene copolymer (with butene-1 as comonomer) intended for blow moulding of products with high stiffness and excellent environmental stress crack resistance (ESCR).The grade contains antioxidant and acid scavenger.

### Applications

**TIPELIN 7300B** is recommended for the blow moulding of jerry cans for the packaging of aggressive industrial chemicals bounded to UN certificates. The grade is recommended for sheet extrusion as well.

**TIPELIN 7300B** is suitable for food contact and for manufacturing of pharmaceutical packing products. The product complies with Food Contact and Pharmaceutical Regulations.

### Properties

	Test method	Unit	Typical value
Melt Mass-Flow Rate (MFR) (190 °C /2.16 kg)	ISO 1133	g/10 min	0.06
Melt Mass-Flow Rate (MFR) (190 °C /5.0 kg)	ISO 1133	g/10 min	0.35
Melt Mass-Flow Rate (MFR) (190 °C /21.6 kg)	ISO 1133	g/10 min	10.5
Density (23 °C) *	ISO 1183	kg/m <sup>3</sup>	954
Tensile Strength at Yield *	ISO 527-1,2	MPa	27
Tensile Strain at Yield *	ISO 527-1,2	%	12
Tensile Strength at Break *	ISO 527-2	MPa	30
Tensile Strain at Break *	ISO 527-1,2	%	1200
Flexural Modulus *	ISO 178	MPa	1400
IZOD Impact Strength (notched, 23 °C) *	ISO 180/1A	kJ/m <sup>2</sup>	15
Vicat Softening Temperature *	ISO 306/A 120	°C	127
Shore D Hardness *	ISO 868	-	64
ESCR F50 B (10% Igepal CO-630) *	ASTM D 1693	h	> 750
OIT (200 °C) *	EN 728	min	40

Typical properties, not to be used as specification.

\* Average mechanical property values of several measurements carried out on standard pressed specimens (ISO 293) conditioned at room temperature (ISO 291).

TIPELIN TIPOLEN TIPPLEN TATREN BRALEN

The joint product portfolio of TVK and Slovnaft Petrochemicals provide infinite opportunities

MEMBERS OF THE MOL GROUP



Slovnaft  
PETROCHEMICALS



### Processing

**TIPELIN 7300B** can be used in conventional blow moulding machines. Recommended processing temperature 180-220 °C.

### Storage and Handling

Pellets are packed in 25 kg PE-LD bags and transported on stretch-wrapped pallets at load of polymer 1375 kg. Heat treated pallets are available as well. Transportation in a road silo or rail silo is also available. For more detailed information please contact Slovnaft Petrochemicals and TVK sales representative.

Since polyethylene is a combustible substance, the fire safety rules applicable for combustible materials in warehouses and store rooms should be observed.

If polymer is stored in conditions of high humidity and fluctuating temperatures, then atmospheric moisture can condense inside the packing. If it happened, it is recommended the pellets to be dried before use. During the storage polyethylene should not be exposed to UV radiation. Producer does not take responsibility for any damages caused by adverse storage.

### REACH Statement

Polymers are exempt of REACH registration. However their raw materials which mean monomers, catalysts and most additives have been pre-registered. SPC/TVK is committed to fully respect this new legislation and will only use REACH compliant raw materials. At this point in time SPC/TVK polyethylenes TIPELIN do not contain any substances specifically identified as SVHC at levels greater than 0.1%.

### Safety

See MSDS.

### Recycling

Polyethylene resins are suitable for recycling using modern recycling methods.

In-house production waste should be kept clean to facilitate direct recycling.

### Disclaimer

The information provided in this publication has been compiled to the best of our present knowledge. However, in view of the various applications of polyethylene resins and the equipments used, the processing conditions may differ.

The recommendations and data herein are to be construed as informatory only and do not relieve users from carrying out their own tests and experiments prior to processing in order to check suitability for a specific use. It is the responsibility of those to whom we supply our products to ensure that any proprietary rights and existing laws and legislation are observed. Our products are under continuous development, therefore we reserve the right to change the information presented in this brochure at our own discretion.

The REACH statement herein does not constitute legal advice. The REACH statement is provided for informational purpose only.

TIPELIN TIPOLEN TIPPLEN TATREN BRALEN

The joint product portfolio of TVK and Slovnaft Petrochemicals provide infinite opportunities

MEMBERS OF THE MOL GROUP



Slovnaft  
PETROCHEMICALS



## MANUFACTURER

TVK Plc.  
 Polymer Business Unit  
 H-3581 Tiszaújváros,  
 P.O. Box: 20  
 Hungary  
 Internet: <http://www.tvk.hu>  
 E-mail: [tvkinfo@tvk.hu](mailto:tvkinfo@tvk.hu)

## CUSTOMER SERVICE

TVK Plc.  
 Polymer Marketing and Sales  
 Customer Service  
 H-3581 Tiszaújváros,  
 P.O. Box: 20  
 Hungary  
 Fax: + 36 49 521-186  
 E-mail: [customerservice@tvk.hu](mailto:customerservice@tvk.hu)

### Customer service for PE

Telephone: + 36 49 521-367, + 36-80 204-249,

### Customer service for PP

Telephone: + 36 49 522-013, + 36-80 204-248

## SALES ORGANIZATION

TVK Plc.  
 Polymer Marketing and Sales Department  
 H-3581 Tiszaújváros,  
 P.O. Box: 20  
 Hungary  
 Telephone: +36 49 521-355  
 Fax: +36 49 522-410  
 E-mail: [polymersales@tvk.hu](mailto:polymersales@tvk.hu)

TIPELIN TIPOLEN TIPPLEN TATREN BRALEN

The joint product portfolio of TVK and Slovnaft Petrochemicals provide infinite opportunities

MEMBERS OF THE MOL GROUP



**TVK Inter-Chemol GmbH.**

Felnerstrasse 5.  
D-60322 Frankfurt am Main  
Germany  
Telephone: +49 69 154 04 12  
Fax: +49 69 154 04 41  
E-mail: [gaboragoston@tvkic.de](mailto:gaboragoston@tvkic.de)

**TVK Italia S.r.L.**

Via P. Teulié 1.  
I-20136 Milano  
Italy  
Telephone: +39 02 58 30 5523  
Fax: +39 02 58 30 3492  
E-mail: [tvkitaly@energy.it](mailto:tvkitaly@energy.it)

**TVK-France**

182 Avenue Charles DeGaulle  
F-92200 Neuilly-sur-Seine  
France  
Telephone: +33 14 745 63 60  
Fax: +33 14 745 45 10  
E-mail: [kacsandi@free.fr](mailto:kacsandi@free.fr)  
[tvk.france@orange.fr](mailto:tvk.france@orange.fr)

**TVK Ukraine**

04128 Kiev  
ul. Tupoleva, 19, office 303  
Telephone: +380 44 374 00 80  
Fax: +380 44 374 00 90  
E-mail: [office@tvkukraine.eu](mailto:office@tvkukraine.eu)

**TVK Polska Sp. z o.o.**

ul. Wawozowa 23/12  
PL 02-796 Warszawa  
Poland  
Telephone: +48 22 545 70 70  
Fax: +48 22 545 70 60  
E-mail: [tvkpolska@tvkpolska.pl](mailto:tvkpolska@tvkpolska.pl)  
[www.tvkpolska.pl](http://www.tvkpolska.pl)

**MOL- Austria Handels GmbH.**

Gartenbaupromenade 2/6  
A-1010 Wien  
Austria  
Telephone: +43 1 515 991 120  
+43 1 515 991 121  
Fax: +43 1 513 37 55 1120  
+43 1 513 37 55 1121  
E-mail: [JHauk@MOL.hu](mailto:JHauk@MOL.hu)

**SC. MOL Romania P.P. SRL**

Str. Danielopolu 4-6  
ET2 Sector 1 Cod 014 134  
Bucuresti, Romania  
Telephone: +40 21 204 85 00  
+40 21 204 85 02  
Fax: +40 21 232 10 59  
E-mail: [ematei@molromania.ro](mailto:ematei@molromania.ro)  
[petchem@molromania.ro](mailto:petchem@molromania.ro)

**Other European Countries**

H-3581 Tiszaújváros  
P.O.B. 20.  
Telephone: +36 49 52 21 18  
Fax: +36 49 52 24 10  
E-mail: [plokai@tvk.hu](mailto:plokai@tvk.hu)

June 2009

TIPELIN TIPOLEN TIPPLEN TATREN BRALEN

The joint product portfolio of TVK and Slovnaft Petrochemicals provide infinite opportunities

MEMBERS OF THE MOL GROUP



Slovnaft  
PETROCHEMICALS

